Elastollan® 2180 A 10

Thermoplastic Polyurethane Elastomer (Ester/Ether) Elastogran GmbH

General		
Material Status	Commercial: Active	
Availability	Europe	
Forms	Pellets	

Physical	Nominal Value Unit	Test Method
Density	1.13 g/cm³	ISO 1183
Mechanical	Nominal Value Unit	Test Method
Tensile Stress (Break)	45.0 MPa	ISO 527-2
Tensile Strain (Break)	450 %	ISO 527-2
Elastomers	Nominal Value Unit	Test Method
Tensile Stress (100% Strain)	4.50 MPa	ISO 37
Tear Strength	40 kN/m	ISO 34-1
Hardness	Nominal Value Unit	Test Method
Shore Hardness (Shore A)	77	ISO 868
Additional Information		

Note: These properties were tested in accordance with the DIN test standard. Stress at 20% elongation, DIN 53504: 1.7 Mpa
Abrasion Loss, DIN 53516: 45 mm³
Stress at 10% elongation, DIN 53504: 1 Mpa
Stress at 50% elongation, DIN 53504: 3.2 Mpa
Stress at 150% elongation, DIN 53504: 5.5 Mpa

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注:以上原料物性数据由IDES发布,我公司仅提供参考!数据如有变动,请联系原料生产厂家获知。我公司不承担任何法律责任!