## Styropor® BFL 322 Expanded Polystyrene BASF Corporation

## Product Description

Styropor BF products can be used in a wide variety of applications including blocks for panels, general insulation, below grade use, fabrication, flotation, and general packaging. Additional applications include insulated concrete forms, thin walled custom molding, and other general protective packaging.

Modified expandable polystyrene (EPS) containing approximately 3.5 wt% pentane as the blowing agent.

Styropor BF products are compatible with many anti-stat, mineral oil and color additives added during processing.

Block molding applications, especially suited for excellent surface cut appearance.

Seneral			
Material Status	<ul> <li>Commercial: Active</li> </ul>		
Availability	<ul> <li>Europe</li> </ul>	<ul> <li>North America</li> </ul>	
Additive	<ul> <li>Blowing Agent (3.5%) <sup>1</sup></li> </ul>		
Features	Foamable	<ul> <li>Good Surface Finish</li> </ul>	
Uses	<ul><li>Flotation Devices</li><li>Insulation</li></ul>	<ul><li>Packaging</li><li>Reinforced Panels</li></ul>	Thin-walled Parts
Agency Ratings	<ul> <li>ASTM C 578, I</li> </ul>	<ul> <li>ASTM E 84</li> </ul>	
Forms	<ul> <li>Spheres</li> </ul>		
Processing Method	Injection Molding		

Physical	Nominal Value Unit			
Apparent Density	0.02 to 0.08 g/cm³			
Moisture Content	< 1.2 %			
Flammability	Nominal Value Unit	Test Method		
Flame Rating - UL	HF-1	UL 94		
UL File Number	E54675			
Additional Information	Nominal Value Unit			
Bead Diameter (> 97%)	600.000 to 1200.000 µm			

## Notes

<sup>1</sup> Pentane

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注:以上原料物性数据由IDES发布,我公司仅提供参考!数据如有变动,请联系原料生产厂家获知。我公司不承担任何法律责任!

<sup>&</sup>lt;sup>2</sup> Typical properties: these are not to be construed as specifications.