

Product Information	<h1 style="margin: 0;">Preliminary</h1> <h2 style="margin: 0;">Ultradur[®] B</h2> <h3 style="margin: 0;">4520 Z High Speed</h3> <h3 style="margin: 0;">PBT</h3> <p style="margin: 0;">(Polybutylene Terephthalate)</p>	 <p style="margin: 0;">BASF The Chemical Company</p>
----------------------------	---	---

PHYSICAL	ISO Test Method	Property Value
Moisture, %	62	
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
Tensile stress at break, MPa	527	
Flexural Strength, MPa	178	
Flexural Modulus, MPa	178	
IMPACT	ISO Test Method	Property Value
Izod Notched Impact, kJ/m ²	180	
Note		

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe

any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！