## Ultramid® B 3M6 BK60564 (Cond) Polyamide 6

## **BASF Corporation**

## Product Description

Ultramid B3M6 BK60564 is a 30% mineral reinforced, pigmented black injection molding PA6 grade for industrial items requiring high impact strength and very high dimensional stability, excellent laser markability.

Seneral Seneral			
Material Status	Commercial: Active		
Availability	North America		
Filler / Reinforcement	Mineral Filler, 30% Filler by Weight		
Additive	Heat Stabilizer		
Features	<ul> <li>Good Abrasion Resistance</li> <li>Good Chemical Resistance</li> <li>Good Dimensional Stability</li> <li>Good Flow</li> <li>Good Processability</li> <li>Good Processability</li> <li>Good Stiffness</li> <li>Good Thermal Aging</li> <li>Resistance</li> <li>Heat Stabilized</li> <li>High Impact Resistance</li> <li>Low Warpage</li> <li>Oil Resistant</li> <li>Semi Crystalline</li> <li>High Impact Resistance</li> <li>Low Viscosity</li> </ul>		
Uses	<ul> <li>Automotive Applications</li> <li>Industrial Applications</li> <li>Protective Coverings</li> <li>Wheels</li> </ul>		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		

Impact	Nominal Value Unit	Test Method
Notched Izod Impact (23°C)	150 J/m	ASTM D256

## Notes

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注:以上原料物性数据由厂家发布,我公司仅提供参考!数据如有变动,请联系原料生产厂家获知。我公司不承担任何法律责任!

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.