



# Product Data Sheet

## DuraStar Polymer DS1010, Natural

### Application/Uses

- Appliances
- Floor care
- Furniture/Furniture trim
- Housewares
- Refrigerator interior components
- Toys/Sporting goods
- Washing machine components
- Writing instruments

### Key Attributes

- Excellent clarity
- Excellent flow
- Fast drying times
- Good chemical resistance
- Outstanding impact resistance
- Quick cycle times

### Product Description

*Durastar* DS1010 polymer contains a mold release. It has excellent appearance and clarity. Its most outstanding features are chemical resistance and excellent processing characteristics. Exposure to aromatic oils often causes crazing or actual fracture of many polymer resins, but DS1010 maintains its physical properties when exposed to these oils, and its appearance is virtually unchanged. Easy to process, it flows readily, fills intricate molds, and is well suited for thick-wall applications. Under existing United States Food and Drug Administration (FDA) regulations, *Durastar* DS1010 may be used in food contact articles which comply with the specifications and conditions of use in 21 CFR 177.1240. This product is certified to ANSI/NSF Standard 51.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED®.

The GREENGUARD INDOOR AIR QUALITY CERTIFIED® Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments. For more information about GEI and to obtain printable certificates for *Eastman* Copolyesters, visit <http://www.greenguard.org/>. Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

### Typical Properties

Specific Gravity	D 792	1.2
Density	ISO 1183	1.19
Mold Shrinkage Parallel to Flow, 3.2-mm (0.125-in.) thickness	D 955	0.002-0.006 mm/mm (0.002-0.006 in./in.)
Tensile Stress @ Yield	D 638	47 MPa (6900 psi)
Tensile Stress @ Break	D 638	51 MPa (7400 psi)
Elongation @ Yield	D 638	5%
Elongation @ Break	D 638	300%
Flexural Modulus	D 790	2000 MPa (2.9 )
Flexural Yield Strength	D 790	69 MPa (10000 psi)
Rockwell Hardness, R Scale	D 785	103
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	80 J/m (1.5 ft·lbf/in.)
@ -40°C (-40°F)	D 256	40 J/m (0.7 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	42 J (31 ft·lbf)

@ -40°C (-40°F)

D 3763

48 J (35 ft·lbf)

Tensile Strength @ Yield	ISO 527	47 MPa
Tensile Strength @ Break	ISO 527	46 MPa
Elongation @ Yield	ISO 527	4%
Elongation @ Break	ISO 527	200%
Tensile Modulus	ISO 527	1800 MPa
Flexural Modulus	ISO 178	1850 MPa
Flexural Strength	ISO 178	65 MPa
Izod Impact Strength, Notched		
@ 23°C	ISO 180	7.8
@ -40°C	ISO 180	4.8
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C	ISO 6603-2	58.7 J
@ -40°C	ISO 6603-2	52.6 J

Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	75°C (167°F)
@ 1.82 MPa (264 psi)	D 648	65°C (149°F)
UL Flammability Classification <sup>d</sup> 3.0 mm specimen	UL 94	94V-2

Deflection Temperature		
@ 0.455 MPa (66 psi)	ISO 75	72°C
@ 1.82 MPa (264 psi)	ISO 75	66°C

Haze	D 1003	0.3%
Regular Transmittance	D 1003	89%
Total Transmittance	D 1003	91%

Drying Temperature		71°C (160°F)
Drying Time		3-4 hrs
Processing Melt Temperature		232-277°C (450-530°F)
Mold Temperature		16-38°C (60-100°F)

**Comments**

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

31-Dec-2002 2:15:20 PM